

## Test protocol


Customer: SMK  
Job number: 132504  
Type and description: TKM 2  
Test speed: 4 mm/min

Material: Galvanised steel  
Test type: Lateral test

## Test results:

| Number | F <sub>max</sub><br>N | dL at F <sub>max</sub><br>mm |
|--------|-----------------------|------------------------------|
| 1      | 2920                  | 19.8                         |
| 2      | 3240                  | 11.0                         |
| 3      | 3610                  | 16.7                         |
| 4      | 3900                  | 9.5                          |
| 5      | 3170                  | 13.6                         |

## Series graphic:



## Statistics:

| Series<br>n = 5 | F <sub>max</sub><br>N | dL at F <sub>max</sub><br>mm | F <sub>break</sub><br>N | dL at break<br>mm |
|-----------------|-----------------------|------------------------------|-------------------------|-------------------|
| x               | 3370                  | 14.1                         | 1040                    | 22.0              |