

Test protocol (standing steel beam)


Customer: SMK
Job number: 132504
Type and description: TKM 2
Test speed: 4 mm/min

Material: Galvanised steel
Test type: Lateral test

Test results:

Number	F _{max} N	dL at F _{max} mm
1	2920	19.8
2	3240	11.0
3	3610	16.7
4	3900	9.5
5	3170	13.6

Series graphic:



Statistics:

Series n = 5	F _{max} N	dL at F _{max} mm	F _{break} N	dL at break mm
x	3370	14.1	1040	22.0